



DEPARTMENT OF REGULATORY AND ECONOMIC RESOURCES (RER)
BOARD AND CODE ADMINISTRATION DIVISION

NOTICE OF ACCEPTANCE (NOA)

MIAMI-DADE COUNTY
PRODUCT CONTROL SECTION

11805 SW 26 Street, Room 208
Miami, Florida 33175-2474
T (786)315-2590 F (786) 31525-99

www.miamidade.gov/economy

CertainTeed Corporation
1400 Union Meeting Road, P.O. Box 1100
Blue Bell, PA 19422-0761

SCOPE:

This NOA is being issued under the applicable rules and regulations governing the use of construction materials. The documentation submitted has been reviewed and accepted by Miami-Dade County RER - Product Control Section to be used in Miami Dade County and other areas where allowed by the Authority Having Jurisdiction (AHJ).

This NOA shall not be valid after the expiration date stated below. The Miami-Dade County Product Control Section (In Miami Dade County) and/or the AHJ (in areas other than Miami Dade County) reserve the right to have this product or material tested for quality assurance purposes. If this product or material fails to perform in the accepted manner, the manufacturer will incur the expense of such testing and the AHJ may immediately revoke, modify, or suspend the use of such product or material within their jurisdiction. RER reserves the right to revoke this acceptance, if it is determined by Miami-Dade County Product Control Section that this product or material fails to meet the requirements of the applicable building code.

This product is approved as described herein, and has been designed to comply with the Florida Building Code including the High Velocity Hurricane Zone of the Florida Building Code.

DESCRIPTION: CertainTeed Conventional Built-Up-Roof Systems Over Steel Decks.

LABELING: Each unit shall bear a permanent label with the manufacturer's name or logo, city, state and following statement: "Miami-Dade County Product Control Approved", unless otherwise noted herein.

RENEWAL of this NOA shall be considered after a renewal application has been filed and there has been no change in the applicable building code negatively affecting the performance of this product.

TERMINATION of this NOA will occur after the expiration date or if there has been a revision or change in the materials, use, and/or manufacture of the product or process. Misuse of this NOA as an endorsement of any product, for sales, advertising or any other purposes shall automatically terminate this NOA. Failure to comply with any section of this NOA shall be cause for termination and removal of NOA.

ADVERTISEMENT: The NOA number preceded by the words Miami-Dade County, Florida, and followed by the expiration date may be displayed in advertising literature. If any portion of the NOA is displayed, then it shall be done in its entirety.

INSPECTION: A copy of this entire NOA shall be provided to the user by the manufacturer or its distributors and shall be available for inspection at the job site at the request of the Building Official.

This NOA revises NOA No. 11-0511.01 and consists of pages 1 through 16.
The submitted documentation was reviewed by Jorge L. Acebo.



NOA No.: 13-0204.13
Expiration Date: 06/19/18
Approval Date: 06/13/13
Page 1 of 16

ROOFING SYSTEM APPROVAL

Category: Roofing
Sub-Category: Built-Up Roofing
Material: Fiberglass
Deck Type: Steel
Maximum Design Pressure -67.5 psf

TRADE NAMES OF PRODUCTS MANUFACTURED OR LABELED BY APPLICANT:

TABLE 1

<u>Product</u>	<u>Dimensions</u>	<u>Test Specification</u>	<u>Product Description</u>
All Weather/ Empire Base Sheet	39 ³ / ₈ " x 65'10"	ASTM D4601 Type II UL Type G2	Fiberglass reinforced, asphalt coated base/ply sheet
Flexiglas Base Sheet	39 ³ / ₈ " x 98'9"	ASTM D4601 Type II UL Type G2	Fiberglass reinforced, SBS modified bitumen base/ply sheet.
Flintlastic Poly SMS Base Sheet	39 ³ / ₈ " x 64'3"	ASTM D4601 Grade S Type II UL Type G2	Polyester reinforced, SBS modified bitumen base/ply sheet.
Glasbase Base Sheet	39 ³ / ₈ " x 98'9"	ASTM D4601 UL Type G2	Fiberglass reinforced, asphalt coated base/ply sheet
Flintlastic Base 20	39 ³ / ₈ " x 49'6"	ASTM D6163 Grade S Type I	Fiberglass reinforced, SBS modified bitumen base/ply sheet.
Flintlastic Ultra Poly SMS Base Sheet	39 ³ / ₈ " x 32'10"	ASTM D6164 Grade S Type I	Polyester reinforced, SBS modified bitumen base/ply sheet.
Black Diamond Base Sheet	39 ³ / ₈ " x 68'7"	ASTM D1970	Self-adhering, fiberglass reinforced, SBS modified bitumen base/ply sheet.
Flintglas Ply Sheet Type IV	39 ³ / ₈ " x 164'7"	ASTM D2178 Type IV UL Type G1	Fiberglass reinforced, asphalt impregnated ply sheet
Flintglas Premium Ply Sheet Type VI	39 ³ / ₈ " x 164'7"	ASTM D2178 Type VI UL Type G1	Fiberglass reinforced, asphalt impregnated ply sheet



<u>Product</u>	<u>Dimensions</u>	<u>Test Specification</u>	<u>Product Description</u>
Yosemite® Venting Base Sheet	39 3/8" x 32'10"	ASTM D3909 ASTM D4897 UL Type G3	Mineral Surfaced fiberglass reinforced buffer sheet.
Flintglas Cap	39 3/8" x 32'10"	ASTM D3909	Asphalt impregnated and coated inorganic glass fiber surfaced with mineral granules used as the top ply in conventional built-up roof membranes.
Flintglas Cap CoolStar	39 3/8" x 32'10"	ASTM D3909	Asphalt impregnated and coated inorganic glass fiber surfaced with mineral granules used as the top ply in conventional built-up roof membranes. Covered with reflective CoolStar Coating.

APPROVED INSULATIONS:

Product Name	Product Description	Manufacturer (With Current NOA)
ACFoam-II	Polyisocyanurate foam insulation	Atlas Roofing Corporation
ISO 95+ GL	Polyisocyanurate foam insulation	Firestone Building Products Company, LLC
High Density Wood Fiberboard	Wood fiber insulation board	Generic
Perlite Insulation	Perlite insulation board	Generic
H-Shield	Polyisocyanurate foam insulation	Hunter Panels, LLC
DensDeck, DensDeck Prime	Water resistant gypsum board	Georgia Pacific Gypsum LLC
ENRGY 3, ENRGY 3 25 PSI	Polyisocyanurate foam insulation	Johns Manville Corp.
Fesco Board	Expanded mineral fiber insulation	Johns Manville Corp.
Multi-Max-3 & Multi-Max FA-3	Polyisocyanurate foam insulation	RMax Operating, LLC.
FlintBoard ISO	Polyisocyanurate foam insulation	CertainTeed Corp.
FlintBoard ISO _H	Polyisocyanurate foam insulation	CertainTeed Corp.



APPROVED FASTENERS:

TABLE 3

Fastener Number	Product Name	Product Description	Dimensions	Manufacturer (With Current NOA)
1.	Dekfast #12, #14 & #15 HS	Insulation fastener		SFS Intec, Inc.
2.	Dekfast Galvalume Steel Hex Plate	Galvalume AZ50 steel plate	2 7/8" x 3 1/4"	SFS Intec, Inc.
3.	Dekfast Dekflat Round Plastic Lock Plate	Polypropylene plate	3" x 3 1/4"	SFS Intec, Inc.
4.	#12 Standard Roofgrip & #14 Roofgrip Fasteners	Insulation fastener for wood and steel.		OMG, Inc.
5.	AccuTrac Hextra	Insulation fastener for wood and steel		OMG, Inc.
6.	3 in. Ribbed Galvalume Plate	Galvalume stress plate.	3" round	OMG, Inc.
7.	AccuTrac Plate	Galvalume stress plate.	3" square	OMG, Inc.
8.	UltraFast	Insulation fastener for wood and steel.		Johns Manville Corp.
9.	UltraFast 3" Round Metal Plate	Galvalume steel plate	3" round	Johns Manville Corp.
10.	UltraFast Square Recessed Metal Plate	Galvalume steel plate	3" square	Johns Manville Corp.
11.	UltraFast Plastic Plate	High Density Polyolefin round plate	3" round	Johns Manville Corp.
12.	3 in. Round Metal Plate	Galvalume AZ50 steel plate	3" round	OMG, Inc.
13.	OMG G-2	Galvalume AZ55 steel plate	3.5" round	OMG, Inc.
14.	OMG Plastic Plate	Polypropylene plastic plate	3" round	OMG, Inc.
15.	Trufast #12 DPH & Trufast #14 HD Fastener	Insulation fastener for wood and steel decks		Altenloh, Brinck & Co. U.S., Inc.
16.	Trufast 3" Metal Insulation Plate	Galvalume AZ50 steel plate	3" round	Altenloh, Brinck & Co. U.S., Inc.
17.	FlintFast #12 & #14	Insulation fastener for wood and steel decks		CertainTeed Corp.
18.	FlintFast 3" Insulation Plate	Galvalume AZ50 steel plate	3" round	CertainTeed Corp.



EVIDENCE SUBMITTED:

<u>Test Agency/Identifier</u>	<u>Name</u>	<u>Report</u>	<u>Date</u>
Trinity ERD	TAS 117 (B)	3503.10.06	10/10/06
	TAS 117 (B)	O6490.04.07-R1	06/27/07
	TAS 117 (B)/ ASTM D6862	C8500SC.11.07	11/30/07
	TAS 114	C8370.08.08	08/19/08
	ASTM Physical Properties	C10080.09.08-R4	03/25/10
	ASTM D4601	C40050.09.12-1	09/28/12
	ASTM D3909	C4420.03.13	03/22/13
	ASTM D1970	C40050.09.12-2	09/28/12
	TAS 114 / TAS 117	3513.08.02-R1	03/17/11
	TAS 114-H / TAS 117-B	C30560.06.10	06/10/10
	TAS 117	C35500.02.11	02/09/11
Momentum Technologies, Inc.	ASTM D 4601	AX31G8D	09/05/08
	ASTM D 3909/ D 4897	AX31G8C	09/05/08
Factory Mutual Research Corp.	4470	J.I. #3Y8A1.AM	09/30/96
	4454	J.I. 0D3A3.AM	04/04/97
	4470	J.I. 2D0A0.AM	12/23/98
	4470	J.I. 1D7A4.AM	11/09/98
	4470	3039046	06/15/10
	4470	3021759	06/03/05
Underwriters Laboratories, Inc.	UL 790	R11656	01/11/13
United States Testing Company	ASTM D 5147	97457-4	06/03/88
	ASTM D 5147	97-457-2R	12/02/87
PRI Construction Materials Technologies LLC	ASTM D6163	CTC-066-02-01	08/09/11
	ASTM D6164	CTC-068-02-01	08/09/11
	ASTM D2178	CTC-122-02-01	03/13/12
	ASTM D2178	CTC-123-02-01	03/13/12
	ASTM D4601	CTC-127-02-01	03/13/12



APPROVED ASSEMBLIES:

Deck Type 2I: Steel, Insulated

Deck Description: 18-22 ga. steel

System Type B(1): Base layer of insulation mechanically fastened, optional top layer adhered with approved asphalt.

All General and System Limitations apply.

One or more layers of any of the following insulations.

Base Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density/ft ²
ACFoam-II, H-Shield, FlintBoard ISO, FlintBoard ISO _H Minimum 1.3" thick	1, 4	1:4 ft ²
ENRGY 3 Minimum 1.4" thick	1, 4, 5, 15 or 17	1:3 ft ²
ISO 95+ GL Minimum 1.4" thick	1, 4, 5, 8, 15 or 17	1:4 ft ²
Approved Perlite Minimum ¾" thick	1 or 4	1:2 ft ²
Approved High Density Wood Fiberboard Minimum ½" thick	1, 4, 15 or 17	1:2 ft ²

Note: Base layer shall be mechanically attached with fasteners and density described above. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density (See Roofing Application Standard RAS 117 for fastening details).

Top Insulation Layer (Optional)	Insulation Fasteners (Table 3)	Fastener Density/ft ²
Any of the insulations listed for Base Layer, above.		
DensDeck, DensDeck Prime Minimum ¼" thick	N/A	N/A

Note: Optional top layer of insulation shall be adhered with approved asphalt within the EVT range and at a rate of 20-40 lbs./100 ft². Please refer to Roofing Application Standard RAS 117 for insulation attachment. Composite insulation boards used as a top layer shall be installed with the polyisocyanurate face down.

Base Sheet: (Optional) Install one ply of All Weather/Empire Base Sheet, Flexiglas Base Sheet or Glasbase Base Sheet directly over the top layer of insulation. Adhere with any approved mopping asphalt at an application rate of 20-35 lbs./sq.

Ply Sheet: Two or more plies of Flintglas Ply Sheet Type IV, Flintglas Premium Ply Sheet Type VI or ASTM D226, Type I sheet adhered in a full mopping of approved asphalt at an application rate of 20-35 lbs./sq.

Cap Sheet: (Optional) One ply of Flintglas Cap or Flintglas Cap CoolStar adhered in a full mopping of approved asphalt at an application rate of 20-35 lbs./sq.

Surfacing: (Required if no cap sheet is used) Any coating, listed below, used as a surfacing must be listed within a current NOA. Install one of the following:

1. Gravel or slag applied at 400 lb./sq. and 300 lb./sq. respectively in a flood coat of approved asphalt at 60 lb./sq.
2. A two part coating consisting of a base coat of APOC #300 Asphalt Fibered Emulsion at rate of 3 gal./sq.; surfaced with 1 gal./sq. APOC#212 Fibered Aluminum Roof Coating.

Maximum Design Pressure: -52.5 psf (See General Limitation #9)

Deck Type 2I: Steel, Insulated

Deck Description: 18-22 ga. steel

System Type B(2): Base layer of insulation mechanically fastened, top layer adhered with approved asphalt.

All General and System Limitations apply.

One or more layers of any of the following insulations.

Base Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density/ft²
ACFoam-II, ENRGY 3, Multi-Max FA-3, H-Shield, FlintBoard ISO, FlintBoard ISO_H		
Minimum 1.5" thick	1, 4, 15 or 17	1:1.33

Note: Base layer shall be mechanically attached with fasteners and density described. Insulation panels listed are minimum sizes and dimensions; if larger panels are used the number of fasteners per board shall be increased maintaining the same fastener density (See Roofing Application Standard RAS 117 for fastening details).

Top Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density/ft²
Fesco Board		
Minimum ¾" thick	N/A	N/A
Approved High Density Wood Fiberboard		
Minimum ½" thick	N/A	N/A

Note: Top layer of insulation shall be adhered with approved asphalt within the EVT range and at a rate of 20-40 lbs./100 ft². Please refer to Roofing Application Standard RAS 117 for insulation attachment. Composite insulation boards used as a top layer shall be installed with the polyisocyanurate face down.

Base Sheet: (Optional) Install one ply of All Weather/Empire Base Sheet, Flexiglas Base Sheet or Glasbase Base Sheet directly over the top layer of insulation. Adhere with any approved mopping asphalt at an application rate of 20-35 lbs./sq.

Ply Sheet: Two or more plies of Flintglas Ply Sheet Type IV or Flintglas Premium Ply Sheet Type VI or ASTM D226, Type I sheet adhered in a full mopping of approved asphalt at an application rate of 20-35 lbs./sq.

Cap Sheet: (Optional) One ply of Flintglas Cap or Flintglas Cap CoolStar adhered in a full mopping of approved asphalt at an application rate of 20-35 lbs./sq.

Surfacing: (Required if no cap sheet is used) Install one of the following:

1. Gravel or slag applied at 400 lb./sq. and 300 lb./sq. respectively in a flood coat of approved asphalt at 60 lb./sq.
2. A two part coating consisting of a base coat of APOC #300 Asphalt Fibered Emulsion at rate of 3 gal./sq.; surfaced with 1 gal./sq. APOC#212 Fibered Aluminum Roof Coating.

Maximum Design

Pressure: -52.5 psf (For Fesco Board) (See General Limitation #7)
-67.5 psf (For High Density Wood Fiberboard) (See General Limitation #7)



Deck Type 2I: Steel, Insulated

Deck Description: 18-22 ga. steel

System Type C(1): All layers of insulation simultaneously fastened.

All General and System Limitations apply.

One or more layers of any of the following insulations:

Base Insulation Layer (Optional)	Insulation Fasteners (Table 3)	Fastener Density/ft²
ACFoam-II, ENRGY 3, Multi-Max-3, H-Shield, FlintBoard ISO, FlintBoard ISO_H Minimum 1" thick	N/A	N/A
Approved Perlite Minimum ¾" thick	N/A	N/A
Approved High Density Wood Fiberboard Minimum ½" thick	N/A	N/A

Note: All layers shall be simultaneously fastened; see top layer below for fasteners and density.

Top Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density/ft²
ACFoam II, FlintBoard ISO Minimum 1.3" thick	1, 4	1:3 ft ²
ENRGY 3, H-Shield, FlintBoard ISO_H Minimum 1.4" thick	1, 4, 15 or 17	1:3 ft ²
Multi-Max-3 Minimum 1.5" thick	1, 4, 5, 15 or 17	1:2.9 ft ²
Approved Perlite Minimum ¾" thick	1, 4, 15 or 17	1:2 ft ²
Approved High Density Wood Fiberboard Minimum ½" thick	1, 4, 15 or 17	1:2 ft ²

Note: All layers of insulation shall be mechanically attached using the fastener density listed above. The insulation panels listed are minimum sizes and dimensions; if larger panels are used, the number of fasteners shall be increased maintaining the same fastener density. Please refer to Roofing Application Standard RAS 117 for insulation attachment.

Base Sheet: (Optional) Install one ply of All Weather/Empire Base Sheet, Flexiglas Base Sheet, Flintlastic Base 20 or Glasbase Base Sheet directly over the top layer of insulation. Adhere with any approved mopping asphalt at an application rate of 20-35 lbs./sq.

Ply Sheet: Two or more plies of Flintglas Ply Sheet Type IV or Flintglas Premium Ply Sheet Type VI or ASTM D226, Type I sheet adhered in a full mopping of approved asphalt at an application rate of 20-35 lbs./sq.

Cap Sheet: (Optional) One ply of Flintglas Cap or Flintglas Cap CoolStar adhered in a full mopping of approved asphalt at an application rate of 20-35 lbs./sq.



Surfacing: (Required if no cap sheet is used) Install one of the following:

1. Gravel or slag applied at 400 lb./sq. and 300 lb./sq. respectively in a flood coat of approved asphalt at 60 lb./sq.
2. A two part coating consisting of a base coat of APOC #300 Asphalt Fibered Emulsion at rate of 3 gal./sq.; surfaced with 1 gal./sq. APOC#212 Fibered Aluminum Roof Coating.

Maximum Design
Pressure: -52.5 (See General Limitation #9)

Deck Type 2I: Steel, Insulated

Deck Description: 18-22 ga., type B, Grade 33 steel, fastened 6" o.c. with puddle welds and washers to steel supports spaced maximum 6 ft. o.c.

System Type C(2): All layers of insulation simultaneously attached.

All General and System Limitations apply.

One or more layers of any of the following insulations.

Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density/ft²
ACFoam-II, ENRGY 3, Multi-Max FA-3, H-Shield, FlintBoard ISO, FlintBoard ISO_H		
Minimum 1.5" thick	1, 4, 15 (#14) or 17 (#14)	1:1.33 ft²

Note: All layers of insulation shall be mechanically attached using the fastener density listed above. The insulation panels listed are minimum sizes and dimensions; if larger panels are used, the number of fasteners shall be increased maintaining the same fastener density. Please refer to Roofing Application Standard RAS 117 for insulation attachment.

Base Sheet: One ply of Black Diamond Base Sheet self-adhered.

Ply Sheet: Two or more plies of Flintglas Ply Sheet Type IV or Flintglas Premium Ply Sheet Type VI or ASTM D226, Type I sheet adhered in a full mopping of approved asphalt at an application rate of 20-35 lbs./sq.

Cap Sheet: (Optional) One ply of Flintglas Cap or Flintglas Cap CoolStar adhered in a full mopping of approved asphalt at an application rate of 20-35 lbs./sq.

Surfacing: (Required if no cap sheet is used) Install one of the following:

1. Gravel or slag applied at 400 lb./sq. and 300 lb./sq. respectively in a flood coat of approved asphalt at 60 lb./sq.
2. A two part coating consisting of a base coat of APOC #300 Asphalt Fibered Emulsion at rate of 3 gal./sq.; surfaced with 1 gal./sq. APOC#212 Fibered Aluminum Roof Coating.

Maximum Design Pressure: -52.5 psf (See General Limitation #7)

Deck Type 2I: Steel, Insulated

Deck Description: 18-22 ga. steel

System Type D(1): All layers of insulation and base sheet simultaneously attached.

All General and System Limitations apply.

One or more layers of any of the following insulations:

Base Insulation Layer (Optional)	Insulation Fasteners (Table 3)	Fastener Density/ft²
ACFoam-II, ENRGY 3, ENRGY 3 25 PSI, H-Shield, FlintBoard ISO, FlintBoard ISO_H Minimum 1.5" thick	N/A	N/A
Approved Perlite Minimum ¾" thick	N/A	N/A
Approved High Density Wood Fiberboard Minimum ½" thick	N/A	N/A
DensDeck, DensDeck Prime Minimum ¼" thick	N/A	N/A
Top Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density/ft²
Approved Perlite Minimum ¾" thick	N/A	N/A
Approved High Density Wood Fiberboard Minimum ½" thick	N/A	N/A
DensDeck, DensDeck Prime Minimum ¼" thick	N/A	N/A

Note: All insulation shall have preliminary attachment, prior to the installation of the roofing membrane at a minimum application rate of two fasteners per board for insulation boards having no dimension greater than 4 ft., and four fasteners for any insulation board having no dimension greater than 8 ft.

Base Sheet: One ply of All Weather/Empire Base Sheet, Flexiglas Base Sheet, Flintlastic Base 20 or Glasbase Base Sheet mechanically attached as detailed below.

Fastening #1: OMG #12 Standard Roofgrip or #14 Roofgrip fasteners with OMG 3 in. Round Metal Plates, Dekfast #12, Dekfast #14 or Dekfast #15 HS with Dekfast Galvalume Steel Hex Plates at a 4" side lap 12" o.c. and two rows staggered in the center of the sheet, 24" o.c.

Fastening #2: OMG #12 Standard Roofgrip or #14 Roofgrip fasteners with OMG 3 in. Round Metal Plates, Dekfast #12, Dekfast #14 or Dekfast #15 HS with Dekfast Galvalume Steel Hex Plates at a 4" side lap 12" o.c. and one row in the center of the sheet, 18" o.c.

Ply Sheet: Two or more plies of Flintglas Ply Sheet Type IV or Flintglas Premium Ply Sheet Type VI or ASTM D226, Type I sheet adhered in a full mopping of approved asphalt at an application rate of 20-35 lbs./sq.



Cap Sheet: (Optional) One ply of Flintglas Cap or Flintglas Cap CoolStar adhered in a full mopping of approved asphalt at an application rate of 20-35 lbs./sq.

Surfacing: (Required if no cap sheet is used) Install one of the following:

1. Gravel or slag applied at 400 lb./sq. and 300 lb./sq. respectively in a flood coat of approved asphalt at 60 lb./sq.
2. A two part coating consisting of a base coat of APOC #300 Asphalt Fibered Emulsion at rate of 3 gal./sq.; surfaced with 1 gal./sq. APOC#212 Fibered Aluminum Roof Coating.

Maximum Design Pressure: -45psf. (See General Limitation #9)

Deck Type 2I: Steel, Insulated

Deck Description: 18-22 ga. steel

System Type D(2): All layers of insulation and base sheet simultaneously attached.

All General and System Limitations apply.

One or more layers of any of the following insulations.

Base Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density/ft²
ACFoam-II, ENRGY 3, Multi Max FA-3, H-Shield, FlintBoard ISO, FlintBoard ISO_H or Any approved Polyisocyanurate Listed in Table 2 Minimum 1.5" thick	N/A	N/A
(Optional) Top Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density/ft²
Approved High Density Wood Fiberboard Minimum ½" thick	N/A	N/A
Approved Perlite Minimum ¾" thick	N/A	N/A
DensDeck, DensDeck Prime Minimum ¼" thick	N/A	N/A

Note: All layers of insulation and base sheet shall be simultaneously attached. See base sheet below for fasteners and density. Refer to Roofing Application Standard RAS 117 for insulation attachment requirements. Insulation shall have preliminary attachment, prior to the installation of the roofing membrane. At an application rate of two fasteners per board for insulation boards having no dimension greater than 4 ft., and four fasteners for any insulation board having no dimension greater than 8 ft.

Base Sheet:	One ply of Flexiglas Base Sheet, Flintlastic Base 20, Flintlastic Poly SMS Base Sheet, Flintlastic Ultra Poly SMS Base Sheet or Yosemite Venting Base Sheet mechanically attached as detailed below.
Fastening:	OMG #14 Roofgrip fasteners with OMG 3 in. Round Metal Plates, Dekfast #14 with Dekfast Galvalume Steel Hex Plates, Trufast #14 HD Fasteners with Trufast 3" Metal Insulation Plates, or FlintFast #14 fasteners with FlintFast 3" Insulation Plates at a 4" side lap 6" o.c. and two rows staggered in the center of the sheet, 6" o.c.
Ply Sheet:	(Optional if Cap Sheet used) Two or more plies of Flintglas Type IV, Flintglas Premium Type VI or ASTM D226, Type I sheet adhered in a full mopping of approved asphalt at an application rate of 20-35 lbs./sq.
Cap Sheet:	(Optional) One ply of Flintglas Cap or Flintglas Cap CoolStar adhered in a full mopping of approved asphalt at an application rate of 20-35 lbs./sq.

- Surfacing: (Required if no cap sheet is used) Install one of the following:
1. Gravel or slag applied at 400 lb./sq. and 300 lb./sq. respectively in a flood coat of approved asphalt at 60 lb./sq.
 2. A two part coating consisting of a base coat of APOC #300 Asphalt Fibered Emulsion at rate of 3 gal./sq.; surfaced with 1 gal./sq. APOC#212 Fibered Aluminum Roof Coating.
- Maximum Design Pressure: -67.5 psf (See General Limitation #7)

STEEL DECK SYSTEM LIMITATIONS:

1. If mechanical attachment to the structural deck through the lightweight insulating concrete is proposed, a field withdrawal resistance testing shall be performed to determine equivalent or enhanced fastener patterns and density. All testing and fastening design shall be in compliance with Testing Application Standard TAS 105 and Roofing Application Standard RAS 117, calculations shall be signed and sealed by a Florida registered Professional Engineer, Registered Architect, or Registered Roof Consultant.
2. For steel deck application where specific deck construction is not referenced: The deck shall be a minimum 22 gage attached with 5/8" puddle welds with weld washers at every flute with maximum deck spans of 5 ft. o.c.

GENERAL LIMITATIONS:

1. Fire classification is not part of this acceptance; refer to a current Approved Roofing Materials Directory for fire ratings of this product.
2. Insulation may be installed in multiple layers. The first layer shall be attached in compliance with Product Control Approval guidelines. All other layers shall be adhered in a full mopping of approved asphalt applied within the EVT range and at a rate of 20-40 lbs./sq., or mechanically attached using the fastening pattern of the top layer
3. All standard panel sizes are acceptable for mechanical attachment. When applied in approved asphalt, panel size shall be 4' x 4' maximum.
4. An overlay and/or recovery board insulation panel is required on all applications over closed cell foam insulations when the base sheet is fully mopped. If no recovery board is used the base sheet shall be applied using spot mopping with approved asphalt, 12" diameter circles, 24" o.c.; or strip mopped 8" ribbons in three rows, one at each side lap and one down the center of the sheet allowing a continuous area of ventilation. Encircling of the strips is not acceptable. A 6" break shall be placed every 12' in each ribbon to allow cross ventilation. Asphalt application of either system shall be at a minimum rate of 12 lbs./sq.

Note: Spot attached systems shall be limited to a maximum design pressure of -45 psf.

5. Fastener spacing for insulation attachment is based on a Minimum Characteristic Force (F') value of 275 lbf., as tested in compliance with Testing Application Standard TAS 105. If the fastener value, as field-tested, are below 275 lbf. insulation attachment shall not be acceptable.
6. Fastener spacing for mechanical attachment of anchor/base sheet or membrane attachment is based on a minimum fastener resistance value in conjunction with the maximum design value listed within a specific system. Should the fastener resistance be less than that required, as determined by the Building Official, a revised fastener spacing, prepared, signed and sealed by a Florida registered Professional Engineer, Registered Architect, or Registered Roof Consultant may be submitted. Said revised fastener spacing shall utilize the withdrawal resistance value taken from Testing Application Standards TAS 105 and calculations in compliance with Roofing Application Standard RAS 117.
7. Perimeter and corner areas shall comply with the enhanced uplift pressure requirements of these areas. Fastener densities shall be increased for both insulation and base sheet as calculated in compliance with Roofing Application Standard RAS 117. Calculations prepared, signed and sealed by a Florida registered Professional Engineer, Registered Architect, or Registered Roof Consultant **(When this limitation is specifically referred within this NOA, General Limitation #9 will not be applicable.)**
8. All attachment and sizing of perimeter nailers, metal profile, and/or flashing termination designs shall conform to Roofing Application Standard RAS 111 and applicable wind load requirements.
9. The maximum designed pressure limitation listed shall be applicable to all roof pressure zones (i.e. field, perimeters, and corners). Neither rational analysis, nor extrapolation shall be permitted for enhanced fastening at enhanced pressure zones (i.e. perimeters, extended corners and corners). **(When this limitation is specifically referred within this NOA, General Limitation #7 will not be applicable.)**
10. All products listed herein shall have a quality assurance audit in accordance with the Florida Building Code and Rule 9N-3 of the Florida Administrative Code.

END OF THIS ACCEPTANCE



NOA No.: 13-0204.13
Expiration Date: 06/19/18
Approval Date: 06/13/13
Page 16 of 16